

Technical Information

40-100








High Speed 2K Clear VOC

HS VOC clear for basecoat.

- Time savings during drying and great performance at lower temperatures.
- Designed for user-friendliness: premixed clear coat and easy to use.
- Good finishing.
- Select hardener according to ambient temperature and size of object to be painted. Choose right hardener from temperature chart.

Application

	Mixing Ratio 100:50	100 % by volume 50 % by volume	40-100 50-415, -420, -430 50-430 only in very hot conditions
	Spray viscosity at 20°C		DIN 4: 17-19 s
	Potlife at 20°C		30 min
	Compliant gravity-feed spray gun		
	Nozzle Size		1.2-1.3
	Application Pressure		2 bar
	Number of spray coats		2
	Film thickness		40-50 µm
	Flash off at 20°C		At least 3 min between spray coats
	Application Remark	Alternative application: ½ + 1, half coat followed by full coat without intermediate flash off.	

Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/l of VOC. The VOC content of this product is 419 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.


Technical Information

40-100



High Speed 2K Clear VOC

Drying

	Drying at 20°C	50-415: 3 h 50-420: 3 h 50-430: 3 h
	Drying at 60°C	50-415: 10 min 50-420: 15 min 50-430: 20 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.



Safety advice:

2004/42/IIIB(d)(420)419: The EU limit value for this product (product category: IIB.d) in ready to use form is max 420 g/l of VOC. The VOC content of this product is 419 g/l.

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.